

## Copper sheet neutral corrosion inhibitor MC-P5340

### FEATURE

- No effect on the glossy of copper
- Non chromium neutral corrosion inhibitor
- Can increase the copper material anti-corrosion performance

### TYPICAL

**Recommended dosage:** 10%

**pH:** 6~8

**Applied Temperature:** 50~60°C

### PROPERTIES

**Processing way:** Dipping or spray

**Dipping time:** 2~3 min

### TECHNICAL

①Degreasing---②Water wash---③Weak acid wash---④  
Chemical polishing---⑤Water wash⑥Water wash---⑦  
MC-P5340 dipping/spray---⑧Water wash---⑨Water wash---⑩  
Water wash---(1)Anti-blushing agent---(2)Dry

### PROCESS

Remark: 1. Our company has Anti-blushing agent MCP-530  
which can furtherly increase the anti-corrosion.

### APPLICATION

- Copper sheet, copper material etc

### STORAGE

- Available in 200 kg/ barrel or 25 kg/ barrel

### AND

- Storage period: 12-24 months in closed containers, shady and dry place

### HANDLING